

SALES SPECIFICATION

Calcium Chloride Pellets 90

<u>Property</u>	<u>Minimum</u>	<u>Maximum</u>
Calcium Chloride (wt. %)	90.0	
Total Alkali Chlorides as NaCl (wt. %)		6.0
Total Magnesium as MgCl ₂ (wt. %)		0.5
Calcium Hydroxide (wt. %)		0.2
Passing 3/8 in. (9.5 mm) sieve (wt. %)	100	
Passing No. 4 (4.76 mm) sieve (wt. %)	80	
Passing No. 20 (0.84 mm) sieve (wt. %)		10
Passing No. 30 (0.6 mm) sieve (wt. %)		1
Bulk Density, Tapped (lb/ft ³)	58	66

Effective: 10/01/2009

Material description: white, odorless pellets

Total Alkali Chlorides as NaCl (wt %), Total Magnesium as MgCl₂ (wt %) and Calcium Hydroxide (wt %) limits are shown on an "Active Ingredient" basis.

Meets ASTM D98 and AASHTO M144 requirements.

SS-P9B-01 10/09